

Heubach formulation No. 547-06

01/10

FUNCTION	PRODUCT	PRODUCER	PBW
Poly(meth)acrylate	Degalan PM 559, 45%	Evonik	31.10
Wetting and Dispersing agent	Tego Dispers 655	Tego Chemie	0.35
Mix.			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	10.50
Titanium dioxide	Kronos 2160	Kronos	8.50
Magnesium silicate	Finntalc M15	Mondo Minerals	5.30
Barium sulphate	EWO	Sachtleben	10.90
Calcium carbonate	Socal U1S2	Solvay	1.30
Calcium carbonate	Omycarb 6-AL	Omya	8.25
Solvent	Solvesso 100	Exxon	5.15
Rheology modifier	Bentone SD-2	Elementis	0.20
Grind.			
Poly(meth)acrylate	Degalan PM 559, 45%	Evonik	16.70
Solvent	Solvesso 100	Exxon	1.75
Add.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			25.0
PVC / CPVC			0.7
CPVC			58.8
PVC in %			41.2

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.