

Heubach formulation No. 892-02

11/19

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Polyaspartic	Desmophen NH 1420	Covestro	31.09
Zeolite	UOP-L powder	UOP	3.07
Solvent	Methoxypropyl acetate		3.39
Solvent	Butyl acetate		3.39
Defoamer	BYK-A 530	Byk	0.64
Wetting and Dispersing agent	DISPERBYK-163	Byk	1.39
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	10.50
Titanium dioxide	SACHTLEBEN R-KB-4	Venator	10.18
Chromium oxide green	COLORTHERM GREEN GN-M	LANXESS	7.07
Iron oxide yellow	BAYFERROX 415	LANXESS	1.27
Barium sulphate	EWO	SACHTLEBEN MINERALS	3.86
Rheology modifier	Cab-O-Sil TS 720	Cabot	0.86
Grind with a bead mill.			
Light stabilizer	Tinuvin 292	BASF	0.64
			77.35
Component B			
Curing agent	Desmodur N 3600	Covestro	22.65
			22.65
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			40.9
PVC in %			15.9

Heubach formulation No. 892-02

11/19

SPECIFICATIONS

PVC / CPVC	0.3
Solids in %	92.1
Crosslinking in %	110.0