

Heubach formulation No. 892-03

11/19

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Polyaspartic	Desmophen NH 1420	Covestro	28.61
Zeolite	UOP-L powder	UOP	3.07
Solvent	Methoxypropyl acetate		3.39
Solvent	Butyl acetate		3.39
Defoamer	BYK-A 530	Byk	0.64
Wetting and Dispersing agent	DISPERBYK-163	Byk	1.39
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	13.98
Titanium dioxide	SACHTLEBEN R-KB-4	Venator	10.54
Chromium oxide green	COLORTHERM GREEN GN-M	LANXESS	7.32
Iron oxide yellow	BAYFERROX 415	LANXESS	1.31
Barium sulphate	EWO	SACHTLEBEN MINERALS	3.99
Rheology modifier	Cab-O-Sil TS 720	Cabot	0.89
<b>Grind with a bead mill.</b>			
Light stabilizer	Tinuvin 292	BASF	0.64
			<b>79.16</b>
<b>Component B</b>			
Curing agent	Desmodur N 3600	Covestro	20.84
			<b>20.84</b>
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			40.9
PVC in %			17.6

Heubach formulation No. 892-03

11/19

## SPECIFICATIONS

PVC / CPVC	0.3
Solids in %	92.1
Crosslinking in %	110.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.